

PALINAL

High Technology Paint

223ULTRA

ULTRA RAPIDO ARIA FORNO

ULTRA RAPID OVEN AIR

2004/42/IIB (d) (420) 420

PREPARAZIONE

Preparazione | Preparazione
 Preparazione | Preparazione



RAPPORTO MISCELA

Mixing ratio | Relación de Mezcla
 Proportion de melange | Mischverhältnis

2 : 1

PRODOTTO

Product | Producto | Produit | Produkt

223ULTRA

100 (Vol)

CATALIZZATORE

Hardener | Catalizador | Catalyseur | Katalysator

293.R010 rapido
 293.R020 standard
 293.R030 lento

50 (Vol)

DILUENTE

Thinner | Diluyente | Diluant | Verdunner

-

-

PRODOTTO PRODUCT PRODUIT PRODUCTO PRODUKT 223ULTRA	CATALISI CATALYS IS CATALYSE CATÁLISIS KATALYSE 293.R010 - 293.R020 - 293.R030	DILUIZIONE DILUTION DILUTION DILUCION VERDÜNNUNG -
--	--	--

50 g	25 g	
100 g	50 g	
150 g	75 g	
200 g	100 g	
250 g	125 g	
300 g	150 g	
350 g	175 g	
400 g	200 g	
450 g	225 g	
500 g	250 g	
600 g	300 g	
700 g	350 g	
800 g	400 g	
900 g	450 g	
1000 g	500 g	

I dati si riferiscono all'applicazione Standard | Data refer to standard application | Les données se réfèrent à l'application standard | Los datos se refieren a la aplicación Standard | Die Daten beziehen sich auf die Standardanwendung

TDS D111 ED. 10/2024

APPLICAZIONE	
Applicazioni Applicazione Applicazioni Applicazioni	
	POT Pot life (20° C) Vie en pot (20° C) Topfzeit (20° C)
	VISCOSITÀ APPLICAZIONE Spraying viscosity Viscosidad de aplicación Viscosité d'application Verarbeit viscositat
	REGOLAZIONE DELLA PISTOLA Airbrush adjustment ajuste del aerógrafo réglage à l'aérographe Airbrush-Einstellung
	UGELLO Nozzle Boquilla Buse Duse
	PRESSIONE ARIA Air Pressure presión de aire Pression d'application Luft
	NUMERO MANI Number of coats Numero de capas Nombre des couches Spritzgänge
	INTERVALLO TRA LE MANI Intervallo Intervallo Intervallo Intervallo

ESSICCAZIONE & RESA	
Carteggiatura Carteggiatura Carteggiatura Carteggiatura	
	APPASSIMENTO Flash time Tiempo de secado Desséchement Abluftzeit
	FUORI POLVERE Dry dust free Hors poussière Fuera polvo Staubtrocken
	PRONTO AL MONTAGGIO Ready to use Prêt pour le montage Listo para el montaje Montagefest
	ESSIC. COMPLETA * Through drying 20°C Sec en profondeur Durckgetrocknet 60°C
	IR - ONDE MEDIE IR - Medium Waves IR - Onde moyennes IR - Ondas medias IR - Mittlere Wellen IR - IRRADIANTI A GAS IR - Gas-fired radiant heaters IR - Radiants gaz IR - Radiantes a gas IR - Gas-Strahler
	LUCIDABILITA' Polishability at 20 °C Polissabilité à 20° C Pulido a 20°C Schleifbar bei 20°C Polishability at 60 °C Polissabilité à 60° C Pulido a 60°C Schleifbar bei 60°C
	SPESSORE FILM SECCO Dry film thickness Espesor de la pelicula seca Epaisseur du film sec Trockenschichtstarke
	RESA RFU -M² / KG x 1 µ Yield RFU Rendement RFU Rendimiento RFU Ergiebigkeit RFU

* Per resistenze chimico/fisiche reticolazione completa a 20°C : 7 giorni |
 For chemical/physical resistance full cross-linking at 20°C : 7 days |
 Pour la résistance chimique/physique réticulation complète à 20°C : 7 jours |
 Para resistencias químicas/físicas reticulación completa a 20 °C : 7 días |
 Erhalt vollständiger chemischer und physikalischer Festigkeit nach kompletter Vernetzung bei 20 °C : 7 Tage

TDS D111 ED. 10/2024

CONSERVABILITA'Ageing | Tiempo de la conservación
Conservabilite | Haltbarkeit**CONSERVABILITA'**Ageing | Tiempo de la conservación
Conservabilite | Haltbarkeit24 mesi months | meses | mois | Monaten
5°C < tC° > 35°C**PRODOTTI COMPLEMENTARI**

| Complementary products | Produits complémentaires | Productos complementarios | Komplementäres Produkt

CATALIZZATORE

Hardener | Catalyseur | Catalizador | Katalysator

DILUENTE

Thinner | Diluant | Diluyente | Verdünner

293.R020 Standard**293.R010** Rapido | Fast | Rapide | Rápido | Schnell**293.R030** Lento | Slow | Lent | Lento | Langsam